

Analysis HTO

P.A.M

ANALYSIS	UNIT	TEST METHOD	RESULT
Density@ 15 °c	KG/M3	ASTM D4052	869
Viscosity 40°C	cst	ASTM D445	34
Viscosity 100°C	cst	ASTM D445	5/6
Pour Point	°C	ASTM D97	-9
Flash Point	°C	ASTM D92	216
Viscosity Index	°C	ASTM D2270	103
Color	°C	ASTM D1500	2